

河北方大包装股份有限公司
FANGDA PACKAGING CO.,LTD.(HEBEI,CHINA)

中國
河北省石家莊市
元氏大街 405 號

No. 405, Yuanshi Street,
Shijiazhuang, Hebei,
China. 051134

Tel : +86 311 86538681
Fax : +86 311 86538685
E-mail:sales@hbfd.cn

Data sheet for Mailing bags

**Hereby we provide the data sheet for the mailing bags provided to B.N.T
Scandinavia AB**

Co-Extruded PE mailing bags
70% virgin PE +30% recycled PE

	Sample width	Sample thickness	Elongation At break	Max Force	Tensile strength (σ M)	original gauge length	Direction
Unit	mm	mm	%	N	MPa	mm	
Sample1	15	0.05	680.20	19.52	20.50	50	longitudinal
Sample2	15	0.051	690.80	20.82	22.12	50	longitudinal
Average value	15.0000	0.0505	685.50	20.17	21.31	50.	

	Sample width	Sample thickness	Elongation At break	Max Force	Tensile strength (σ M)	original gauge length	Direction
Unit	mm	mm	%	N	MPa	mm	
Sample1	15	0.05	560.46	18.22	21.84	50	Horizontal
Sample2	15	0.052	588.76	21.46	24.20	50	Horizontal
Average value	15	0.051	574.61	19.84	23.02	50	

FANGDA PACKAGING CO.,LTD.(HEBEI,CHINA)
2019.7